



Material - UNI G22Ni10

Standard Specification for Low Alloy Steel With Low Temperature Toughness for Castings Subject to Pressure

Group - Ferrous Mild Steel Alloys

Sub Group - UNI G22Ni10 Low Alloy Steel With Low Temperature Toughness for Castings Subject to Pressure Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.250 max.		
Silicon	Si %	0.600 max.		
Manganese	Mn %	0.800 max.		
Phosphorus	P %	0.035 max.	Normalising + Tempering or Hardening + Tempering	
Sulphur	S %	0.035 max.		
Nickel	Ni %	2.000 - 3.000		
Iron	Fe %	Balance		
-	-	-		
-	/-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	440 min.
-	-	-	Yield Strength in Mpa	275 min.
-	-	-	Elongation in %	21 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impa <mark>ct in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
SA-352 LC2	ASME	USA	Casting	
1.5635	DIN	Germany	Steel	
J22500	UNS	USA	Casting	
G9Ni10	AFNOR NF	France	Casting	
SCPL 21	JIS	Japan	Casting	
F.8373	UNE	Spain	Casting	
A352 LC2	ASTM	USA	Casting	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.