



Material - UNI X 1 NiCrMoCu 25-20-5

Standard Specification for Seemless Steel Tubes for Pressure Purposes

Group - Ferrous Stainless Steel Alloys

Sub Group - UNI X 1 NiCrMoCu 25-20-5 Seemless Steel Tubes for Pressure Purposes
Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries
Grade Belongs to the Industry - Steel, Sheet, Plate and Strip

Chemical Composition			Heat Treatment	
Carbon	C %	0.020 max.	Solution Annealing	
Silicon	Si %	0.700 max.		
Manganese	Mn %	2.000 max.		
Phosphorus	P %	0.030 max.		
Sulphur	S %	0.010 max.		
Chromium	Cr %	19.000 - 21.000		
Molybdenum	Mo %	4.000 - 5.000		
Nickel	Ni %	24.000 - 26.000		•
Copper	Cu %	1.200 - 2.000	Mechanical Properties	
Nitrogen	N %	0.150 max.	Tensile Strength in Mpa	500 - 2100
Iron	Fe %	Balance	Yield Strength in Mpa	220 min.
-	-	-	Elongation in %	20 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HB	230 max.
-	-	-	Impac <mark>t in Joule</mark>	60 J @ RT

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
10216-5 EN 1.4539	BS	British	Tube	
1.4539	DIN	Germany	Steel, Bar and Rod	
1.4539	EN	European Union	Steel, Bar and Rod	
X1NiCrMoCu25-20-5	AFNOR NF	France	Steel	
X1NiCrMoCu25-20-5	DIN	Germany	Steel, Bar and Rod	
-	-	-	1	
-	-	-	-	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.