



Material - UNI X 12 Cr 9 KG

Standard Specification for Seamless Steel Tubes for Pressure Purposes

Group - Ferrous Stainless Steel Alloys

Sub Group - UNI X 12 Cr 9 KG Seamless Steel Tubes for Pressure Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Steel and Forging

Chemical Composition			Heat Treatment	
Carbon	C %	0.150 max.	Isothermal Annealing	
Silicon	Si %	0.500 - 1.000		
Manganese	Mn %	0.300 - 0.600		
Phosphorus	P %	0.030 max.		
Sulphur	S %	0.030 max.		
Chromium	Cr %	8.000 - 10.000		
Molybdenum	Mo %	0.900 - 1.100		
Iron	Fe %	Balance		
-	-	-		
			Mechanical Properties	
			Tensile Strength in Mpa	640 - 890
			Yield Strength in Mpa	480 min.
			Elongation in %	15 min.
			Reduction of Area in %	-
			Hardness in HB	280 max.
			Impact in Joule	30 J @ RT

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
1.7386+I	EN	European Union	Steel and Tube
1.7386+I	DIN	Germany	Steel and Tube
1.7386+I	DIN	Germany	Steel and Tube
X11CrMo91TA	ISO	International	Steel and Tube
X11CrMo91TN+TT	ISO	International	Steel and Tube
X12CrMo9 1	DIN	Germany	Steel and Tube
17116	CSN	Czech Republic	Steel

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.