



Material - UNI X 2 CrNiMoN 25-7-4

Standard Specification for Seemless Steel Tubes for Pressure Purposes

Group - Ferrous Stainless Steel Alloys

Sub Group - UNI X 2 CrNiMoN 25-7-4 Seemless Steel Tubes for Pressure Purposes
Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries
Grade Belongs to the Industry - Steel, Bar and Rods

Chemical Composition			Heat Treatment	
Carbon	C %	0.030 max.		
Silicon	Si %	1.000 max.		
Manganese	Mn %	2.000 max.	Solution Annealing	
Phosphorus	P %	0.035 max.		
Sulphur	S %	0.015 max.		
Chromium	Cr %	24.000 - 26.000		
Molybdenum	Mo %	3.000 - 4.500		
Nickel	Ni %	6.000 - 8.000		_
Nitrogen	N %	0.200 - 0.350	Mechanical Properties	
Iron	Fe %	Balance	Tensile Strength in Mpa	730 - 2100
-	-	-	Yield Strength in Mpa	500 min.
-	-	-	Elongation in %	15 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HB	310 max.
-	-	-	Impac <mark>t in Joule</mark>	60 J @ RT

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
10216-5 EN 1.4410	BS	British	Tube	
1.441	EN	European Union	Steel, Sheet, Plate and Strip	
1.441	DIN	Germany	Steel, Sheet, Plate and Strip	
X2CrNiMoN25-7-4	AFNOR NF	France	Steel	
X2CrNiMoN25-7-4	DIN	Germany	Steel, Sheet, Strip and Plate	
X2CrNiMoN25 7 4	EN	European Union	Steel and Forging	
S32750	UNS	USA	Steel	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.