



Material - UNI X 2 CrNiN 23-4

Standard Specification for Seamless Steel Tubes for Pressure Purposes

Group - Ferrous Stainless Steel Alloys

Sub Group - UNI X 2 CrNiN 23-4 Seamless Steel Tubes for Pressure Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Steel, Sheet, Plate and Strip

Chemical Composition			Heat Treatment	
Carbon	C %	0.030 max.	Solution Annealing	
Silicon	Si %	1.000 max.		
Manganese	Mn %	2.000 max.		
Phosphorus	P %	0.035 max.		
Sulphur	S %	0.015 max.		
Chromium	Cr %	22.000 - 24.000		
Molybdenum	Mo %	0.100 - 0.600		
Nickel	Ni %	3.500 - 5.500		
Copper	Cu %	0.100 - 0.600		
Nitrogen	N %	0.050 - 0.200		
Iron	Fe %	Balance	Mechanical Properties Tensile Strength in Mpa 600 - 2100 Yield Strength in Mpa 385 min. Elongation in % 20 min. Reduction of Area in % - Hardness in HB 290 max. Impact in Joule 60 J @ RT	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
10216-5 EN 1.4362	BS	British	Tube
1.4362	EN	European Union	Steel, Bar and Rod
1.4362	DIN	Germany	Steel, Bar and Rod
X2CrNiN23 4	EN	European Union	Steel, Bar and Rod
X2CrNiN23 4	AFNOR NF	France	Steel
X2CrNiN23 4	DIN	Germany	Steel, Bar and Rod
X2CrNiN 234	ISO	International	Steel, Bar, Rolling and Forging

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.