



Material - UNS D50950

Standard Specification for Alloy Steel Casting

Group - Ferrous Mild Steel Alloys
Sub Group - UNS D50950 Alloy steel casting
Application - Intended for Valve, Pump, General Engineering, A

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Phosphorus	P %	0.050 max.	Annealing or Normalising or Hardening + Tempering	
Sulphur	S %	0.050 max.		
Iron	Fe %	Balance		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-	Mechanical Properties	
-	/ -		Tensile Strength in Mpa	-
-	-	-	Yield Strength in Mpa	655 min.
-	-	-	Elongation in %	-
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country Grade Belong to the Industry		
A148 Grade 80-50	ASTM	USA	Casting	
A148 Grade 90-60	ASTM	USA	Casting	
A148 Grade 105-85	ASTM	USA	Casting	
A148 Grade 160-145	ASTM	USA	Casting	
A148 Grade 130-115	ASTM	USA	Casting	
Grade 135-125	ASTM	USA	Casting	
A148 Grade 115-95	ASTM	USA	Casting	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.