



Material - UNS GX2CrNiMoN25-7-3

Standard Specification for Steel Castings for Pressure Purposes

Group - Ferrous Stainless Steel Alloys

Sub Group - UNS GX2CrNiMoN25-7-3 Steel Castings for Pressure Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.030 max.		
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.500 max.	Solution Annealing	
Phosphorus	P %	0.030 max.		
Sulphur	S %	0.020 max.		
Chromium	Cr %	24.000 - 26.000		
Molybdenum	Mo %	3.000 - 4.000		
Nickel	Ni %	6.000 - 8.500		_
Tungsten	W %	1.000 max.	Mechanical Properties	
Copper	Cu %	1.000 max.	Tensile Strength in Mpa	650 - 900
Nitrogen	N %	0.150 - 0.250	Yield Strength in Mpa	400 min.
Iron	Fe %	Balance	Elongation in %	22 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impac <mark>t in Joule</mark>	50 J @ RT

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
1.4417	EN	European Union	Casting	
1.4417	DIN	Germany	Casting	
1.4417	DIN	Germany	Casting	
GX2CrNiMoN25-7-3	DIN	Germany	Casting	
GX2CrNiMoN25-7-3	EN	European Union	Casting	
GX2CrNiMoN25-7-3	AFNOR NF	France	Casting	
-	-	-	-	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.