



Material - UNS J02500

Standard Specification for Carbon Steel Casting

Group - Ferrous Mild Steel Alloys

Sub Group - UNS J02500 Carbon Steel Casting

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.250 max.	As - Cast	
Silicon	Si %	0.800 max.		
Manganese	Mn %	0.750 max.		
Phosphorus	P %	0.050 max.		
Sulphur	S %	0.060 max.		
Iron	Fe %	Balance		
-	-	-		
-	-	-	Mechanical Properties Tensile Strength in Mpa 415 min. Yield Strength in Mpa 205 min. Elongation in % 24 min. Reduction of Area in % 35 min. Hardness in BHN - Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A27 Grade N-1	ASTM	USA	Casting
A27 Grade U-60-30	ASTM	USA	Casting
A27 Grade 60-30	ASTM	USA	Casting
A27 Grade 65-35	ASTM	USA	Casting
A27 Grade 70-36	ASTM	USA	Casting
A27 Grade 70-40	ASTM	USA	Casting
A27 Grade N-2	ASTM	USA	Casting

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.