



Material - UNS J22090

Standard Specification for Alloy Steel Casting

Group - Ferrous Mild Steel Alloys

Sub Group - UNS J22090 Alloy Steel Casting

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.200 max.	Normalising or Annealing or Hardening + Tempering	
Silicon	Si %	0.600 max.		
Manganese	Mn %	0.500 - 0.800		
Phosphorus	P %	0.350 max.		
Sulphur	S %	0.030 max.		
Chromium	Cr %	2.000 - 2.750		
Molybdenum	Mo %	0.900 - 1.200		
Iron	Fe %	Balance		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	585 min.
-	-	-	Yield Strength in Mpa	380 min.
-	-	-	Elongation in %	20 min.
-	-	-	Reduction of Area in %	35 min.
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
1.7375	DIN	Germany	Tube
1.7380	EN	European Union	Bar, Plate and Forging
10 CD 9-10	AFNOR NF	France	Plate
10 CrMo 10	STAS	Romania	Tube
10 CrMo 9-10	MSZ	Hungary	Bar, Tube and Forging
10 CrMo 9-10	BS	British	Steel
A356 10	ASTM	USA	Casting

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.