



## Material - UNS J23055

## **Standard Specification for Alloy Steel Casting**

**Group - Ferrous Mild Steel Alloys** 

Sub Group - UNS J23055 Alloy Steel Casting

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

**Grade Belongs to the Industry - Casting** 

Chemical Composition			Heat Treatment	
Carbon	C %	0.250 - 0.350		
Silicon	Si %	0.200 - 0.800		
Manganese	Mn %	0.400 - 0.700		
Phosphorus	P %	0.040 max.	Annealing or Normalising or Hardening + Tempering	
Sulphur	S %	0.450 max.		
Chromium	Cr %	0.700 - 0.900		
Nickel	Ni %	1.650 - 2.000		
Molybdenum	Mo %	0.200 - 0.300		
Tungsten	W %	0.100 max.	Mechanical Properties	
Copper	Cu %	0.500 max.	Tensile Strength in Mpa	1030 min.
Iron	Fe %	Balance	Yield Strength in Mpa	793 min.
-	-	-	Elongation in %	7 min.
-	-		Reduction of Area in %	-
-	-		Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table					
Material	Standard	Country	Grade Belong to the Industry		
AISI 4330	AISI	USA	Forging, Bar, Wire, and Shape		
4330	SAE	USA	Bar, Tube, Sheet, Strip and Forging		
4340	AMS	USA	Bar and Forging		
A732 9Q	ASTM	USA	Casting		
J23015	UNS	USA	Casting		
A487 10A	ASTM	USA	Casting		
SA 487 10A	ASME	USA	Casting		

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.