



Material - UNS J23259

Standard Specification for Alloy Steel Casting

Group - Ferrous Mild Steel Alloys
Sub Group - UNS J23259 Alloy Steel Casting

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.280 -0.330		
Silicon	Si %	0.300 - 0.600	As- Cast or Normalising or Annealing or Hardening + Tempering	
Manganese	Mn %	0.600 - 0.900		ancaling or Hardoning ±
Phosphorus	P %	0.035 max.		•
Sulphur	S %	0.040 max.		iiig
Chromium	Cr %	0.700 - 0.900		
Molybdenum	Mo %	0.200 - 0.300		
Nickel	Ni %	1.650 - 2.000		-
Iron	Fe %	Balance	Mechanical Properties	
-	-		Tensile Strength in Mpa	-
-	-	-	Yield Strength in Mpa	-
-	-	-	Elongation in %	-
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table				
Material	Standard	Country	Country Grade Belong to the Industry	
A915 Grade SC 4330	ASTM	USA	Casting	
4330	AISI	USA	Bar, Wire, Tube and Forging	
4330	SAE	USA	Bar, Wire, Tube and Forging	
4330	AS	Australia	Bar, Wire, Tube and Forging	
4330	AMS	USA	Bar, Wire, Tube and Forging	
4340	AS	Australia	Steel	
-	-	-	-	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.