



## Material - UNS J24053

## **Standard Specification for Alloy Steel Casting**

Group - Ferrous Mild Steel Alloys
Sub Group - UNS J24053 Alloy Steel Casting

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade	Belongs	to the	Industry	/ - Casting
-------	---------	--------	----------	-------------

Chemical Composition			Heat Treatment	
Carbon	C %	0.380 - 0.430		
Silicon	Si %	0.300 - 0.600		
Manganese	Mn %	0.600 - 0.900	As Cast or Normalising or Ar	ancaling or Hardoning I
Phosphorus	P %	0.035 max.	As- Cast or Normalising or Annealing or Hardening + Tempering	
Sulphur	S %	0.040 max.		
Chromium	Cr %	0.700 - 0.900		
Molybdenum	Mo %	0.200 - 0.300		
Nickel	Ni %	1.650 - 2.000		
Iron	Fe %	Balance	Mechanical Pr	roperties
-	-		Tensile Strength in Mpa	-
-	-		Yield Strength in Mpa	-
-	-	-	Elongation in %	-
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table						
Material	Standard	Country	Grade Belong to the Industry			
A915 Grade SC 4340	ASTM	USA	Casting			
4340	AISI	USA	Bar, Wire, Tube and Forging			
4340	AS	USA	Bar, Wire, Tube and Forging			
4340	AMS	USA	Bar, Wire, Tube and Forging			
4340	SAE	USA	Bar, Wire, Tube and Forging			
A 29 4340	ASTM	USA	Bar, Wire, Tube and Forging			
A 505 4340	ASTM	USA	Bar, Wire, Tube and Forging			

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.