



Material - UNS J41501

Standard Specification for Alloy Steel Casting

Group - Ferrous Mild Steel Alloys

Sub Group - UNS J41501 Alloy Steel Casting

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.150 max.	Normalising + Tempering or Hardening + Tempering	
Silicon	Si %	0.600 max.		
Manganese	Mn %	0.500 - 0.800		
Phosphorus	P %	0.025 max.		
Sulphur	S %	0.025 max.		
Chromium	Cr %	0.400 max.		
Nickel	Ni %	4.000 - 5.000		
Molybdenum	Mo %	0.250 max.		
Copper	Cu %	0.500 max.		
Vanadium	V %	0.030 max.		
Iron	Fe %	Balance	Mechanical Properties Tensile Strength in Mpa 485 - 655 Yield Strength in Mpa 275 min. Elongation in % 24 min. Reduction of Area in % 35 min. Hardness in BHN - Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
SA-352 Grade LC4	ASME	USA	Casting
AM8Ni18	UNE	Spain	Casting
J14500	UNS	Spain	Casting
F.8375	UNE	Spain	Casting
A575 B4N B4Q	ASTM	USA	Casting
A352 LC4	ASTM	USA	Casting
-	-	-	-

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.