



Material - UNS J92110

Standard Specification for Alloy Steel Casting

Group - Ferrous Stainless Steel Alloys
Sub Group - UNS J92110 Alloy Steel Casting
Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries
Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.070 max.		
Silicon	Si %	1.000 max.		
Manganese	Mn %	0.700 max.		
Phosphorus	P %	0.035 max.	Normalising or Annealing or Hardening + Tempering	
Sulphur	S %	0.030 max.		
Chromium	Cr %	14.000 - 15.000		
Nickel	Ni %	4.200 - 5.500		
Copper	Cu %	2.500 - 3.200		
Nitrogen	N %	0.050 max.	Mechanical Properties	
Niobium	Nb %	0.150 - 0.350	Tensile Strength in Mpa	1170 min.
Iron	Fe %	Balance	Yield Strength in Mpa	1000 min.
-	-	-	Elongation in %	5 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HB	375 min.
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
J92180	UNS	USA	Casting	
SA-747 CB7Cu-2	ASME	USA	Casting	
5356	AMS	USA	Casting	
AMS 5346	SAE	USA	Casting	
5400	AMS	USA	Casting	
5357	AMS	USA	Casting	
A747 CB7CU-2	ASTM	USA	Casting	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.