



Material - UNS J92805

Standard Specification for Alloy Steel Casting

Group - Ferrous Stainless Steel Alloys
Sub Group - UNS J92805 Alloy Steel Casting
Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries
Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.080 max.		
Silicon	Si %	1.500 max.		
Manganese	Mn %	1.500 max.		
Phosphorus	P %	0.040 max.	Solution Annealing	
Sulphur	S %	0.040 max.		
Chromium	Cr %	23.000 - 26.000		
Nickel	Ni %	8.000 - 11.000		
Molybdenum	Mo %	0.500 max.		_
Nitrogen	N %	0.200 - 0.300	Mechanical Properties	
-	-		Tensile Strength in Mpa	-
-	-	-	Yield Strength in Mpa	-
-	-	-	Elongation in %	-
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
J92802	UNS	USA	Casting	
ASTM A 451 Grade CPE20N	ASTM	USA	Centrifugal Cast Steel Pipes	
A351 CE20N	ASTM	USA	Casting	
-	-	-	-	
-	-	-	-	
-	-	-	-	
-	-	-	-	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.