



Material - UNS J93254

Standard Specification for Austenitic Chromium Nickel Molybdenum Cuprum Nitrogen Stainless Steel Casting

Group - Ferrous Stainless Steel Alloys

Sub Group - UNS J93254 Austenitic Chromium Nickel Molybdenum Cuprum Nitrogen Stainless Steel Casting

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.025 max.	Solution Annealing	
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.200 max.		
Phosphorus	P %	0.045 max.		
Sulphur	S %	0.010 max.		
Chromium	Cr %	19.500 - 20.500		
Nickel	Ni %	17.500 - 19.700		
Molybdenum	Mo %	6.000 - 7.000		
Nitrogen	N %	0.180 - 0.240		
Copper	Cu %	0.500 - 1.000		
-	-	-	Mechanical Properties Tensile Strength in Mpa 550 min. Yield Strength in Mpa 260 min. Elongation in % 35 min. Reduction of Area in % - Hardness in BHN - Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A351 CK3MCuN	ASTM	USA	Casting
Z4Cmd 19.13M	AFNOR NF	France	Casting
317 C 12	BS	British	Casting
422940	CSN	Czech Republic	Casting
J92810	UNS	USA	Casting
SA-351 CK3MCuN	ASME	USA	Casting
A351 CE20	ASTM	USA	Casting

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.