



## Material - UNS J93373

### Standard Specification for Cast Duplex Chromium Nickel Copper Molybdenum Nitrogen Stainless Steel

Group - Ferrous Stainless Steel Alloys

Sub Group - UNS J93373 Cast Duplex Chromium Nickel Copper Molybdenum Nitrogen Stainless Steel

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment			
Carbon	C %	0.030 max.	Solution Annealing			
Silicon	Si %	1.100 max.				
Manganese	Mn %	1.200 max.				
Phosphorus	P %	0.030 max.				
Sulphur	S %	0.030 max.				
Chromium	Cr %	24.000 - 26.700				
Nickel	Ni %	5.600 - 6.700				
Molybdenum	Mo %	2.900 - 3.800				
Nitrogen	N %	0.220 - 0.330				
Copper	Cu %	1.400 - 1.900				
Iron	Fe %	Balance	<th colspan="2">Mechanical Properties</th>		Mechanical Properties	
-	-	-	Tensile Strength in Mpa	690 min.		
-	-	-	Yield Strength in Mpa	450 min.		
-	-	-	Elongation in %	25 min.		
-	-	-	Reduction of Area in %	-		
-	-	-	Hardness in BHN	-		
-	-	-	Impact in Joule	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A240 S32205	ASTM	USA	Plate, Sheet and Strip
A276 S32205	ASTM	USA	Bar and Shapes
A988 S32205	ASTM	USA	Casting
J92205	UNS	USA	Casting
J93372	UNS	USA	Casting
A995 1B	ASTM	USA	Casting
A890 1B	ASTM	USA	Casting

**Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email [marketing@gravitycastindia.com](mailto:marketing@gravitycastindia.com)**

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.