



Material - UNS N06050

Standard Specification for Castings, Nickel Chromium Alloy Solid Solution Strengthened

Group - Ferrous Stainless Steel Alloys

Sub Group - UNS N06050 Castings, Nickel Chromium Alloy Solid Solution Strengthened

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.400 - 0.600	As - Cast	
Silicon	Si %	0.500 - 2.000		
Manganese	Mn %	1.500 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.040 max.		
Chromium	Cr %	15.000 - 19.000		
Molybdenum	Mo %	0.500 max.		
Nickel	Ni %	64.000 - 68.000		
Iron	Fe %	Balance		
-	-	-		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	415 min.
-	-	-	Yield Strength in Mpa	-
-	-	-	Elongation in %	-
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A608 Grade HX 50	ASTM	USA	Casting
G X 55 NiCr 60-12	UNI	Italy	Casting
N06006	UNS	USA	Casting
A297 Grade HX	ASTM	USA	Casting
IS 4522 Grade 14	IS	India	Casting
13505 Grade HX	IS	India	Casting
-	-	-	-

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.