



Material - UNS N08030

Standard Specification for Casting Ni-Fe-Cr Alloy Solid Solution Strengthened

Group - Ferrous Stainless Steel Alloys

Sub Group - UNS N08030 Casting Ni-Fe-Cr Alloy Solid Solution Strengthened

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.250 - 0.350	Solution Annealing	
Silicon	Si %	2.500 max.		
Manganese	Mn %	2.000 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.040 max.		
Chromium	Cr %	13.000 - 17.000		
Nickel	Ni %	33.000 - 37.000		
Molybdenum	Mo %	0.500 max.		
Iron	Fe %	Balance	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	440 min.
-	-	-	Yield Strength in Mpa	195 min.
-	-	-	Elongation in %	13 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A351 HT30	ASTM	USA	Casting
SA-351 HT30	ASME	USA	Casting
N08603	UNS	USA	Casting
7806 Grade 12	IS	India	Casting
SCH 16	JIS	Japan	Casting
SA-351 Grade HT 30	ASME	USA	Casting
HT-30	NBR	Brazil	Steel

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.