



Material - UNS N08151

Standard Specification for Cast Iron Nickel Chromium Columbium Austenitic Stainless Steel Casting

Group - Ferrous Stainless Steel Alloys

Sub Group - UNS N08151 Cast Iron Nickel Chromium Columbium Austenitic Stainless Steel Casting

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.050 - 0.150	Soft Annealing, Cast	
Silicon	Si %	0.500 - 1.500		
Manganese	Mn %	0.150 - 1.500		
Phosphorus	P %	0.030 max.		
Sulphur	S %	0.030 max.		
Chromium	Cr %	19.000 - 21.000		
Nickel	Ni %	31.000 - 34.000		
Niobium	Nb %	0.500 - 1.500		
Iron	Fe %	Balance		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	435 min.
-	-	-	Yield Strength in Mpa	170 min.
-	-	-	Elongation in %	20 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
1.4859	DIN	Germany	Casting
G X 40 NiCrSiNb 38-18	DIN	Germany	Casting
G X 10 NiCrNb 32-20	DIN	Germany	Casting
SA-351 CT15C	ASME	USA	Casting
N08004	UNS	USA	Casting
1.4849	DIN	Germany	Casting
A351 CT15C	ASTM	USA	Casting

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.