



Material - UNS S32750

Standard Specification for Seamless Steel Tubes for Pressure Purposes

Group - Ferrous Stainless Steel Alloys

Sub Group - UNS S32750 Seamless Steel Tubes for Pressure Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Steel

Chemical Composition			Heat Treatment	
Carbon	C %	0.030 max.	Solution Annealing	
Silicon	Si %	0.800 max.		
Manganese	Mn %	1.200 max.		
Phosphorus	P %	0.035 max.		
Sulphur	S %	0.020 max.		
Chromium	Cr %	24.000 - 26.000		
Molybdenum	Mo %	3.000 - 5.000		
Nickel	Ni %	6.000 - 8.000		
Nitrogen	N %	0.240 - 0.320		
Iron	Fe %	Balance		
-	-	-	Mechanical Properties Tensile Strength in Mpa 730 - 2100 Yield Strength in Mpa 500 min. Elongation in % 15 min. Reduction of Area in % - Hardness in HB 310 max. Impact in Joule 60 J @ RT	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
10216-5 EN 1.4410	BS	British	Tube
1.441	EN	European Union	Steel, Sheet, Plate and Strip
1.441	DIN	Germany	Steel, Sheet, Plate and Strip
X2CrNiMoN25-7-4	AFNOR NF	France	Steel
X2CrNiMoN25-7-4	DIN	Germany	Steel, Sheet, Strip and Plate
X2CrNiMoN25-7-4	UNI	Italy	Steel, Bar and Rod
X2CrNiMoN25 7 4	EN	European Union	Steel and Forging

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.