



**GRAVITY CAST PVT. LTD.**  
**GRAVITY GROUP OF COMPANIES**

## Material - UNS S43035

**Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet, and Strip for Pressure Vessels and for General Applications**

**Group - Ferrous Stainless Steel Alloys**

**Sub Group - UNS Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications**

**Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries**

**Grade Belongs to the Industry - Steel**

Chemical Composition			Heat Treatment	
Carbon	C %	0.030 max.	Annealing or Hardening + Tempering	
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.000 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.030 max.		
Chromium	Cr %	17.000 - 19.000		
Nickel	Ni %	0.500 max.		
Nitrogen	N %	0.030 max.		
Titanium	Ti %	$0.200 + 4(C+N) - 1.100$ max.		
Aluminium	Al %	0.150 max.		
Iron	Fe %	Balance	Tensile Strength in Mpa	415 min.
-	-	-	Yield Strength in Mpa	205 min.
-	-	-	Elongation in %	22 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	183 max.
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A240 UNS S43035	ASTM	USA	Steel, Plate, Sheet and Strip
A959 S43035	ASTM	USA	Steel
439	SAE	USA	Steel
A479 439	ASTM	USA	Steel and Bar
A803 Grade TP 439	ASTM	USA	Steel and Tube
A959 Type 439	ASTM	USA	Steel
SA-240 439	ASME	USA	Steel

**Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email [marketing@gravitycastindia.com](mailto:marketing@gravitycastindia.com)**

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

**ONE STOP SOLUTION FOR METAL PARTS**