



Material - UNS S44660

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet, and Strip for Pressure Vessels and for General Applications

Group - Ferrous Stainless Steel Alloys

Sub Group - UNS Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Steel

Chemical Composition			Heat Treatment	
Carbon	C %	0.030 max.	Annealing or Hardening + Tempering	
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.000 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.030 max.		
Chromium	Cr %	25.000 - 28.000		
Nickel	Ni %	1.000 - 3.500		
Molybdenum	Mo %	3.000 - 4.000		
Nitrogen	N %	0.040 max.		
Ti + Cb	Ti % + Cb %	0.200 - 1.000		
Iron	Fe %	Balance	Mechanical Properties Tensile Strength in Mpa 585 min. Yield Strength in Mpa 450 min. Elongation in % 18 min. Reduction of Area in % - Hardness in BHN 241 max. Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A240 UNS S44660	ASTM	USA	Steel, Plate, Sheet and Strip
A176 S44660	ASTM	USA	Steel, Sheet, Plate and Strip
SA-240 UNS S44660	ASME	USA	Steel
A268 26-3-3	ASTM	USA	Steel and Tube
A959 Type 26-3-3	ASTM	USA	Steel
SA-803 26-3-3	ASME	USA	Steel and Tube
SA-240 Type 26-3-3	ASME	USA	Steel, Sheet, Plate and Strip

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.