



Material - AFNOR NF A50-452 A5

Standard Specification for Aluminium and Aluminium Alloys. Coil coating strip and sheet

Group - Non-Ferrous Aluminium Alloy

Sub Group - AFNOR NF A50-452 Aluminium and Aluminium Alloys. Coil coating strip and sheet

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Coil, Strip and Sheet

Chemical Composition			Heat Treatment	
Copper	Cu %	0.050 max.	As-Cast	
Magnesium	Mg %	0.050 max.		
Lead	Pb %	0.050 max.		
Tin	Sn %	0.050 max.		
Silicon	Si %	0.250 max.		
Iron	Fe %	0.400 max.		
Manganese	Mn %	0.050 max.		
Titanium	Ti %	0.030 max.		
Zinc	Zn %	0.050 max.		
Other	Ot%	0.030 max.		
Aluminium	Al %	99.500 min.	Mechanical Properties Tensile Strength in Mpa 60 - 160 Yield Strength in Mpa 20 - 125 Elongation in % 4 - 35 Reduction of Area in % - Hardness in HB - Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
3.025	DIN	Germany	Ingot
1050A	EN	European Union	Wire
Al 99.5	ISO	International	Casting
1050A	UNI	Italy	Wire
A5	LMO	BS	British
Ingot and Casting	CSN	Czech Republic	Wire
-	-	-	-

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.