



Material - AFNOR NF A51-115 CuZn40Pb

Standard Specification for Copper and Copper Alloy Plates, Sheets and Circles for Heat Exchangers

Group - Non-Ferrous Copper Alloy

Sub Group - AFNOR NF A51-115 Copper and Copper Alloy Plates, Sheets and Circles for Heat Exchangers

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Plate and Sheet

Chemical Composition			Heat Treatment	
Iron	Fe %	0.150 max.	Normalizing or Annealing or Tempering	
Other	Ot%	0.500 max.		
Lead	Pb %	0.400 - 0.900		
Tin	Sn %	0.250 max.		
Copper	Cu %	58.000 - 61.000		
Zinc	Zn %	Balance		
-	-	-		
-	-	-	Mechanical Properties Tensile Strength in Mpa 340 min. Yield Strength in Mpa 125 min. Elongation in % 28 min. Reduction of Area in % - Hardness in BHN - Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
CuZn40Pb	AFNOR NF	France	Plate
CuZn37Pb	IS	India	Plate
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.