



## Material - AFNOR NF C-NiCr16Mo16

### Standard Specification for Castings, Nickel and Nickel Alloy

Group - Non-Ferrous Nickel Alloys

Sub Group - AFNOR NF C-NiCr16Mo16 Castings, Nickel and Nickel Alloy

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.020 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.800 max.		
Manganese	Mn %	1.000 max.		
Phosphorus	P %	0.030 max.		
Sulphur	S %	0.030 max.		
Chromium	Cr %	15.000 - 17.500		
Tungsten	W %	1.000 max.		
Molybdenum	Mo %	15.000 - 17.500		
Iron	Fe %	2.000 max.	Mechanical Properties	
Nickel	Ni %	Balance	Tensile Strength in Mpa	495 min.
-	-	-	Yield Strength in Mpa	275 min.
-	-	-	Elongation in %	20 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A 494 CW2M	ASTM	USA	Casting
SA-494 CW2M	ASME	USA	Casting
NC16D16-M	AFNOR NF	France	Casting
NC6455	AFNOR NF	France	Casting
N26455	UNS	USA	Casting
-	-	-	-
-	-	-	-

**Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email [marketing@gravitycastindia.com](mailto:marketing@gravitycastindia.com)**

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.