

Material - AFNOR NF C-NiFe30Cr20Mo3CuNb

Standard Specification for Castings, Nickel and Nickel Alloy

Group - Non-Ferrous Nickel Alloys

Sub Group - AFNOR NF C-NiFe30Cr20Mo3CuNb Castings, Nickel and Nickel Alloy

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.050 max.		
Silicon	Si %	0.750 - 1.200		
Manganese	Mn %	1.000 max.	As-Cast or Annealing or Age Hardning	
Phosphorus	Р%	0.030 max.		
Sulphur	S %	0.030 max.		
Chromium	Cr %	19.500 - 23.500		
Molybdenum	Mo %	2.500 - 3.500		
Niobium	Nb %	0.700 - 1.000		
Copper	Cu %	1.500 - 3.000	Mechanical Properties	
Iron	Fe %	28.000 - 32.000	Tensile Strength in Mpa	450 min.
Nickel	Ni %	Balance	Yield Strength in Mpa	170 min.
-	-	-	Elongation in %	25 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardn <mark>ess in BH</mark> N	-
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
A 494 CU5MCuC	ASTM	USA	Casting	
SA-494 CU5MCuC	ASME	USA	Casting	
NC8826	AFNOR NF	France	Casting	
N08826	UNS	USA	Casting	
-	-	-	-	
-	-	-	-	
-	-	-	-	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

ONE STOP SOLUTION FOR METAL PARTS