



Material - AFNOR NF CEN/TS 13388 CuNi18Zn27

Standard Specification for Copper and Copper Alloy

Group - Non-Ferrous Copper Alloy

Sub Group - AFNOR NF CEN/TS 13388 Copper and Copper Alloy

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Plate, Sheet and Strip

Chemical Composition			Heat Treatment	
Iron	Fe %	0.300 max.		
Manganese	Mn %	0.500 max.		
Nickel	Ni %	17.000 - 19.000	Normalizing or Annealing or Tempering	
Other	Ot%	0.200 max.		
Lead	Pb %	0.030 max.		
Tin	Sn %	0.030 max.		
Copper	Cu %	53.000 - 56.000		
Zinc	Zn %	Balance		
-	1	-	Mechanical Properties	
-	-		Tensile Strength in Mpa	390 - 800
-	-	-	Yield Strength in Mpa	280 - 660
-	-	-	Elongation in %	2 - 30
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HV	90 - 250
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
CuNi18Zn27	IS	India	Rod and Bar	
CuNi18Zn27	ISO	International	Plate, Sheet and Strip	
B122 C77000	ASTM	USA	Plate, Sheet, Strip and Rolled Bar	
B151 C77000	ASTM	USA	Rod and Bar	
B206 C77000	ASTM	USA	Wire	
CuNi18Zn20	ISO	International	Plate, Sheet and Strip	
CuNi18Zn27	DIN	Germany	Plate, Sheet and Strip	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.