



Material - AFNOR NF CuSn4Pb4Zn4

Standard Specification for Copper-Tin Alloy Rod

Group - Non Ferrous Copper Alloys

Sub Group - AFNOR NF CuSn4Pb4Zn4 Copper-Tin Alloy Rod

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Rod

Chemical Composition			Heat Treatment	
Iron	Fe %	0.100 max.	As Raw or Solution Heat Treated	
Nickel	Ni %	0.200 max.		
Phosphorus	P %	0.010 - 0.400		
Lead	Pb %	3.500 - 4.500		
Tin	Sn %	3.500 - 4.500		
Tellurium	Te %	0.200 max.		
Zinc	Zn %	3.500 - 4.500		
Other	Ot %	0.200 max.		
Copper	Cu %	Balance	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	447 min.
-	-	-	Yield Strength in Mpa	350 min.
-	-	-	Elongation in %	5 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	115 - 210
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
CuSn4Pb4Zn4	DIN	Germany	Rod
C 5441 B	JIS	Japan	Rod, Bar and Wire
CuSn4Pb4Zn4	NBN	Belgium	Rod
CW456K	NBN	Belgium	Rod
CW456K	AFNOR NF	France	Rod
CuSn4Pb4Zn4	NS	Norway	Rod
CW456K	NS	Norway	Rod

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.