



Material - AFNOR NF EN 1706 AC-47100

Standard Specification for Aluminium and Aluminium Alloys - Casting

Group - Non-Ferrous Aluminium Alloy

Sub Group - AFNOR NF EN 1706 Aluminium and Aluminium Alloys - Casting

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Copper	Cu %	0.700 -1.200	As-Cast	
Iron	Fe %	1.300 max.		
Magnesium	Mg %	0.350 max.		
Manganese	Mn %	0.550 max.		
Nickel	Ni %	0.300 max.		
Silicon	Si %	10.500 - 13.500		
Lead	Pb %	0.200 max.		
Tin	Sn %	0.100 max.		
Titanium	Ti %	0.200 max.		
Zinc	Zn %	0.550 max.		
Chromium	Cr %	0.100 max.	Mechanical Properties	
Other	Ot%	0.250 max.	Tensile Strength in Mpa	240 min.
Aluminium	Al %	Balance	Yield Strength in Mpa	140 min.
-	-	-	Elongation in %	1 min.
-	-	-	Reduction of Area in %	-
			Hardness in HB	70 min.
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
EN AC-47100	DIN	Germany	Casting
EN AC-47100	BS	British	Casting
EN AC-47100	ASME	USA	Casting
EN AC-47100	UNI	Italy	Casting
Al Si12Cu1(Fe)	ISO	International	Casting
EN AC-47100	UNE	Spain	Casting
EN AC-47100	SFS	Finland	Casting

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.