



Material - AFNOR NF NC0002

Standard Specification for Castings, Nickel and Nickel Alloy

Group - Non-Ferrous Nickel Alloys

Sub Group - AFNOR NF NC0002 Castings, Nickel and Nickel Alloy

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.060 max.		
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.000 max.		
Phosphorus	P %	0.030 max.	As-Cast or Annealing or Age Hardning	
Sulphur	S %	0.030 max.		
Chromium	Cr %	15.500 - 17.500		
Tungsten	W %	3.800 - 5.300		
Molybdenum	Mo %	16.000 - 18.000		
Vanadium	V %	0.200 - 0.400	Mechanical Properties	
Iron	Fe %	4.500 - 7.500	Tensile Strength in Mpa	495 min.
Nickel	Ni %	Balance	Yield Strength in Mpa	275 min.
-	-	-	Elongation in %	4 min.
-	-	-	Reduction of Area in %	-
-	-		Hardness in BHN	-
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
A 494 CW12MW	ASTM	USA	Casting	
SA-494 CW12MW	ASME	USA	Casting	
C-NiMo17Cr16Fe6W4	AFNOR NF	France	Casting	
NC16D16Fe5W5-M	AFNOR NF	France	Casting	
N30002	UNS	USA	Casting	
-	-	-	-	
-	-	-	-	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.