



Material - AFNOR NF NC4135

Standard Specification for Castings, Nickel and Nickel Alloy

Group - Non-Ferrous Nickel Alloys

Sub Group - AFNOR NF NC4135 Castings, Nickel and Nickel Alloy

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.350 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	1.250 max.		
Manganese	Mn %	1.500 max.		
Phosphorus	P %	0.030 max.		
Sulphur	S %	0.020 max.		
Niobium	Nb %	0.500 max.		
Copper	Cu %	26.000 - 33.000		
Iron	Fe %	3.500 max.		
Nickel	Ni %	Balance		
-	-	-		
			Mechanical Properties	
-	-	-	Tensile Strength in Mpa	450 min.
-	-	-	Yield Strength in Mpa	170 min.
-	-	-	Elongation in %	25 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A 494 M35-1	ASTM	USA	Casting
SA-494 M-35-1	ASME	USA	Casting
C-NiCu30	AFNOR NF	France	Casting
NU30-M	AFNOR NF	France	Casting
N04020	UNS	USA	Casting
N24135	UNS	USA	Casting
-	-	-	-

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.