

Material - ANSI/AA 360

Standard Specification for Aluminium Alloy for General Engineering and Light-Weight Structural Purpose

Group - Non-Ferrous Alumium Alloy

Sub Group - ANSI/AA Aluminium Alloy for General Engineering and Light-Weight Structural Purpose Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Casting

Chemical Composition		Heat Treatment	
Si %	9.000 - 10.000		
Fe %	2.000 max.		
Cu %	0.600 max.		
Mg %	0.400 - 0.600	As-Cast	
Mn %	0.350 max.		
Ni %	0.500 max.		
Zn %	0.500 max.		
Sn %	0.150 max.		
Ot%	0.250 max.	Mechanical Properties	
Al %	Balance	Tensile Strength in Mpa	303 min.
-	-	Yield Strength in Mpa	172 min
-	-	Elongation in %	2.5 min.
-	-	Reduction of Area in %	-
-	-	Hardne <mark>ss in BHN</mark>	75 min.
-		Impac <mark>t in Joule</mark>	-
	Si % Fe % Cu % Mg % Mn % Zn % Zn % Zn % Ot% Al % - - -	Si % 9.000 - 10.000 Fe % 2.000 max. Cu % 0.600 max. Mg % 0.400 - 0.600 Mn % 0.350 max. Ni % 0.500 max. Zn % 0.500 max. Ot% 0.250 max. Al % Balance - - - -	Si % 9.000 - 10.000 Fe % 2.000 max. Cu % 0.600 max. Mg % 0.400 - 0.600 As-Cast Mn % 0.350 max. As-Cast Mn % 0.500 max. Ms % Zn % 0.500 max. Mechanical Pro Al % Balance Tensile Strength in Mpa - - Elongation in % - - Hardness in BHN

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
A03600	UNS	USA	Casting	
B 275 360.0	ASTM	USA	Casting	
A 275 SG100B	ASTM	USA	Casting	
B 85 360.0	ASTM	USA	Casting	
B 85 SG100B	ASTM	USA	Casting	
A03600	SAE	USA	Casting	
360.0	NBR	Brazil	Casting	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

ONE STOP SOLUTION FOR METAL PARTS