

Material - ANSI/AA 380

Standard Specification for Aluminium Alloy for General Engineering and Light-Weight Structural Purpose

Group - Non-Ferrous Alumium Alloy

Sub Group - ANSI/AA Aluminium Alloy for General Engineering and Light-Weight Structural Purpose Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Silicon	Si %	7.500 - 9.500		
Iron	Fe %	2.000 max.	As-Cast or Aging	
Copper	Cu %	3.000 - 4.000		
Magnesium	Mg %	0.300 max.		
Manganese	Mn %	0.500 max.		
Nickel	Ni %	0.500 max.		
Zinc	Zn %	3.000 max.		
Tin	Sn %	0.350 max.		
Other	Ot%	0.500 max.	Mechanical Properties	
Aluminium	Al %	Balance	Tensile Strength in Mpa	317 min.
-	-	-	Yield Strength in Mpa	159 min
-	-	-	Elongation in %	3.5 min.
-	-	_	Reduction of Area in %	-
-	-	-	Hardness in BHN	80 min.
-	-		Impact in Joule	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
A03800	UNS	USA	Casting	
B 275 380.0	ASTM	USA	Casting	
A 275 SC84B	ASTM	USA	Casting	
B 85 380.0	ASTM	USA	Casting	
B 85 SC84B	ASTM	USA	Casting	
A03800	SAE	USA	Casting	
380.0	NBR	Brazil	Casting	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.