

Material - ANSI/AA 383

Standard Specification for Aluminium Alloy for General Engineering and Light-Weight Structural Purpose

Group - Non-Ferrous Alumium Alloy

Sub Group - ANSI/AA Aluminium Alloy for General Engineering and Light-Weight Structural Purpose Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Casting

Chemical Composition		Heat Treatment	
Si %	9.500 - 11.500		
Fe %	1.300 max.		
Cu %	2.000 - 3.000		
Mg %	0.100 max.	As-Cast	
Mn %	0.500 max.		
Ni %	0.300 max.		
Zn %	3.000 max.		
Sn %	0.150 max.		
Ot%	0.500 max.	Mechanical Pro	perties
Al %	Balance	Tensile Strength in Mpa	310 min.
-	-	Yield Strength in Mpa	152 min
-	-	Elongation in %	3.5 min.
-	_	Reduction of Area in %	-
-	-	Hardness in BHN	75 min.
-		Impact in Joule	-
	Si % Fe % Cu % Mg % Mn % Ni % Zn % Ot% Al %	Si % 9.500 - 11.500 Fe % 1.300 max. Cu % 2.000 - 3.000 Mg % 0.100 max. Mn % 0.500 max. Ni % 0.300 max. Zn % 3.000 max. Sn % 0.150 max. Ot% 0.500 max. Al % Balance	Si % 9.500 - 11.500 Fe % 1.300 max. Cu % 2.000 - 3.000 Mg % 0.100 max. Mn % 0.500 max. Ni % 0.300 max. Sn % 0.150 max. Ot% 0.500 max. Al % Balance Tensile Strength in Mpa Yield Strength in Mpa Yield Strength in Mpa Elongation in % Reduction of Area in % Hardness in BHN

Cross Reference Table				
Material	Standard	Country Grade Belong to the Industry		
B 275 383.0	ASTM	USA	Casting	
AA335	AS	Australia	Ingots and Casting	
A03830	UNS	USA	Ingots and Casting	
A03830	SAE	USA	Ingots and Casting	
383.0	NBR	Brazil	Casting	
383.0	NMX	Maxico	Casting	
B 85 SC102A	ASTM	USA	Casting	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.