



Material - ANSI AA 393.0

Standard Specification for Aluminium and Aluminium Alloys Ingot and Casting for General Engineering Purposes

Group - Non-Ferrous Alumium Alloy

Sub Group - ANSI AA 393.0 Aluminium and Aluminium Alloys Ingot and Casting for General Engineering Purposes Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Ingot and Casting

Chemical Composition			Heat Treatment	
Copper	Cu %	0.700 - 1.100		
Magnesium	Mg %	0.700 - 1.300		
Silicon	Si %	21.000 - 23.000		
Iron	Fe %	1.300 max.	As-Cast	
Manganese	Mn %	0.100 max.		
Nickel	Ni %	2.000 - 2.500		
Zinc	Zn %	0.100 max.		
Titanium	Ti %	0.100 - 0.200		
Vanadium	V %	0.080 - 0.150	Mechanical Properties	
Aluminium	Al %	Balance	Tensile Strength in Mpa	120 min.
-	-	-	Yield Strength in Mpa	-
-	-	-	Elongation in %	-
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HB	100 - 140
-	-	-	Impact in Joule	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
LM29	BS	British	Ingot and Casting	
4928-B	IS	India	Casting	
A039300	UNS	USA	Casting	
393.0	NBR	Brazil	Casting	
Vanasil	AA	USA	Casting	
-	-	-	-	
-	-	-	-	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.