



## Material - ANSI AA A357.0

### Standard Specification for Aluminium and Aluminium Alloys Ingot and Casting

Group - Non-Ferrous Aluminium Alloy

Sub Group - ANSI AA A357.0 Aluminium and Aluminium Alloys - Ingot and Casting

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Ingot and Casting

Chemical Composition			Heat Treatment	
Copper	Cu %	0.200 max.	As-Cast	
Magnesium	Mg %	0.400 - 0.700		
Silicon	Si %	6.500 - 7.500		
Iron	Fe %	0.200 max.		
Manganese	Mn %	0.100 max.		
Beryllium	Be %	0.040 - 0.070		
Titanium	Ti %	0.040 - 0.200		
Zinc	Zn %	0.100 max.		
Other	Ot%	0.150 max.		
Aluminium	Al %	Balance		
-	-	-	<b>Mechanical Properties</b> Tensile Strength in Mpa      310 min. Yield Strength in Mpa      250 min. Elongation in %      3 min. Reduction of Area in %      - Hardness in HB      85 - 115 Impact in Joule      -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
LM25	BS	British	Ingot and Casting
AA601	AS	Australia	Ingot and Casting
AA603	AS	Australia	Ingot and Casting
AC601	AS	Australia	Ingot and Casting
AC603	AS	Australia	Ingot and Casting
AP601	AS	Australia	Ingot and Casting
AP603	AS	Australia	Ingot and Casting

**Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email [marketing@gravitycastindia.com](mailto:marketing@gravitycastindia.com)**

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.