



## Material - ANSI/AA C99750

## **Specification Standards for Die Castings**

Group - Non-Ferrous Copper Alloy
Sub Group - ANSI/AA for Die Castings

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

**Grade Belongs to the Industry - Casting** 

Chemical Composition			Heat Treatment	
Lead	Pb %	0.500 - 2.500		
Zinc	Zn %	17.000 - 23.000		
Iron	Fe %	1.000 max.	As-Cast	
Aluminium	Al %	0.250 - 3.000		
Manganese	Mn %	17.000 - 23.000		
Nickel	Ni %	5.000 max.		
Other	Ot%	1.000 max.		
Copper	Cu %	55.000 - 61.000		
-	-	-	Mechanical Properties	
-	-		Tensile Strength in Mpa	448 min.
-	-	-	Yield Strength in Mpa	221 min
-	-	-	Elongation in %	30 min.
-	-	-	Reduction of Area in %	-
-	-		Hardness in BHN	110 min.
-	-	-	Impac <mark>t in Joule</mark>	102 min.

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
-	-	-	-	
-	-	ì	-	
-	-		-	
-	-	-	-	
-	-	-	-	
-	-	-	-	
-	-	-	-	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.