



## Material - ANSI/AA Zamak 3

### Specification Standards for Die Castings

Group - Non-Ferrous Zinc Alloy

Sub Group - ANSI/AA for Die Castings

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	3.700 - 4.300	As-Cast or Aging	
Magnesium	Mg %	0.020 - 0.060		
Copper	Cu %	0.100 max.		
Iron	Fe %	0.050 max.		
Lead	Pb %	0.005 max.		
Cadmium	Cd %	0.004 max.		
Tin	Sn %	0.002 max.		
Zinc	Zn %	Balance		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	283 min.
-	-	-	Yield Strength in Mpa	221 min
-	-	-	Elongation in %	10 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HB	82 min.
-	-	-	Impact in Joule	58 min.

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
ZP3	ISO	International	Casting
Z33521	UNS	USA	Ingot and Casting
B86 Alloy 3	ASTM	USA	Casting
B86 Zamak 3	ASTM	USA	Casting
B86 AG40A	ASTM	USA	Casting
ZnAl4	UNI	Italy	Ingot and Casting
B240 Zamak 3	ASTM	USA	Casting

**Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email [marketing@gravitycastindia.com](mailto:marketing@gravitycastindia.com)**

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.