

## Material - ANSI/AA 13

## Standard Specification for Aluminium Alloy for General Engineering and Light-Weight Structural Purpose

**Group - Non-Ferrous Alumium Alloy** 

Sub Group - ANSI/AA Aluminium Alloy for General Engineering and Light-Weight Structural Purpose Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Silicon	Si %	11.000 - 13.000		
Iron	Fe %	2.000 max.		
Copper	Cu %	1.000 max.	As-Cast	
Magnesium	Mg %	0.100 max.		
Manganese	Mn %	0.350 max.		
Nickel	Ni %	0.500 max.		
Zinc	Zn %	0.500 max.		
Tin	Sn %	0.150 max.		
Other	Ot%	0.250 max.	Mechanical Properties	
Aluminium	Al %	Balance	Tensile Strength in Mpa	296 min.
-	-	-	Yield Strength in Mpa	145 min
-	-	-	Elongation in %	2.5 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	80 min.
-	-		Impact in Joule	-

Cross Reference Table				
Material	Standard	Country	ry Grade Belong to the Industry	
B 275 S12B	ASTM	USA	Casting	
A04130	UNS	USA	Casting	
A04130	SAE	USA	Casting	
B85 S12B	ASTM	USA	Casting	
413.0	NBR	Brazil	Casting	
413.0	NMX	Maxico	Casting	
413.0	SAE	USA	Casting	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.