



Material - ANSI/AA B413.0

Standard Specification for Aluminium and Aluminium Alloys - Ingots and Castings

Group - Non-Ferrous Aluminium Alloy

Sub Group - ANSI/AA Aluminium and Aluminium Alloys - Ingots and Castings

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Ingot and Casting

Chemical Composition			Heat Treatment	
Copper	Cu %	0.100 max.	As-Cast	
Iron	Fe %	0.500 max.		
Magnesium	Mg %	0.050 max.		
Manganese	Mn %	0.350 max.		
Nickel	Ni %	0.050 max.		
Silicon	Si %	11.000 - 13.000		
Titanium	Ti %	0.250 max.		
Zinc	Zn %	0.100 max.		
Aluminium	Al %	Balance		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	160 - 190
-	-	-	Yield Strength in Mpa	55 - 69
-	-	-	Elongation in %	5 - 7
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
BS401	AS	Australia	Ingot and Casting
CA401	AS	Australia	Ingot and Casting
CB401	AS	Australia	Ingot and Casting
CC401	AS	Australia	Ingot and Casting
LM6	BS	British	Casting
4600	IS	India	Ingot and Casting
ADC 2	JIS	Japan	Ingot and Casting

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.