



**GRAVITY CAST PVT. LTD.**  
**GRAVITY GROUP OF COMPANIES**

## Material - AS 1874 303

**Standard Specification for Aluminium and Aluminium Alloy - Ingot and Castings**

**Group - Non-Ferrous Aluminium Alloy**

**Sub Group - AS 1874 Aluminium and Aluminium Alloy - Ingot and Castings**

**Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries**

**Grade Belongs to the Industry - Ingot and Casting**

Chemical Composition			Heat Treatment	
Copper	Cu %	2.000 - 4.000	As-Cast	
Iron	Fe %	0.800 max.		
Fe + Mn	Fe% + Mn%	1.300 max.		
Magnesium	Mg %	0.150 max.		
Manganese	Mn %	0.700 max.		
Nickel	Ni %	0.300 max.		
Lead	Pb %	0.150 max.		
Silicon	Si %	4.000 - 5.000		
Tin	Sn %	0.150 max.		
Zinc	Zn %	0.500 max.		
Chromium	Cr %	0.100 max.	Mechanical Properties	
Titanium	Ti %	0.200 min.	Tensile Strength in Mpa	135 - 275
Other	Ot%	0.200 max.	Yield Strength in Mpa	-
Aluminium	Al %	Balance	Elongation in %	1.5 - 2
-	-	-	Reduction of Area in %	-
			Hardness in BHN	-
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
AA303	AS	Australia	Ingot and Casting
AA339	AS	Australia	Ingot and Casting
LM4	BS	British	Ingot and Casting
4223	IS	India	Ingot and Casting
L-2610	UNE	Spain	Ingot and Casting
-	-	-	-
-	-	-	-

**Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email [marketing@gravitycastindia.com](mailto:marketing@gravitycastindia.com)**

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

**ONE STOP SOLUTION FOR METAL PARTS**