



Material - AS 1874 AP603

Standard Specification for Aluminium and Aluminium Alloys Ingot and Casting

Group - Non-Ferrous Aluminium Alloy

Sub Group - AS 1874 AA601 Aluminium and Aluminium Alloys - Ingot and Casting

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Ingot and Casting

Chemical Composition			Heat Treatment	
Copper	Cu %	0.050 max.	As-Cast	
Magnesium	Mg %	0.450 - 0.700		
Silicon	Si %	6.500 - 7.500		
Iron	Fe %	0.150 max.		
Manganese	Mn %	0.030 max.		
Titanium	Ti %	0.200 max.		
Zinc	Zn %	0.050 max.		
Other	Ot%	0.150 max.		
Aluminium	Al %	Balance		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	270 - 290
-	-	-	Yield Strength in Mpa	-
-	-	-	Elongation in %	1 - 3
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
LM25	BS	British	Ingot and Casting
AA601	AS	Australia	Ingot and Casting
AA603	AS	Australia	Ingot and Casting
AC601	AS	Australia	Ingot and Casting
AC603	AS	Australia	Ingot and Casting
AP601	AS	Australia	Ingot and Casting
A357.0	AA	USA	Ingot and Casting

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.