



## Material - AS 1874 BA701

**Standard Specification for Aluminium and Aluminium Alloys - Ingot and Casting**

**Group - Non-Ferrous Aluminium Alloy**

**Sub Group - AS 1874 Aluminium and Aluminium Alloys - Ingot and Casting**

**Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries**

**Grade Belongs to the Industry - Ingot and Casting**

Chemical Composition			Heat Treatment	
Copper	Cu %	0.150 max.	As-Cast	
Iron	Fe %	0.500 max.		
Magnesium	Mg %	0.500 - 0.700		
Manganese	Mn %	0.150 max.		
Silicon	Si %	0.250 max.		
Titanium	Ti %	0.150 - 0.250		
Zinc	Zn %	4.800 - 5.700		
Chromium	Cr %	0.400 - 0.600		
Nickel	Ni %	0.100 max.		
Lead	Pb %	0.050 max.		
Tin	Sn %	0.050 max.	<b>Mechanical Properties</b> Tensile Strength in Mpa      215 min. Yield Strength in Mpa      - Elongation in %      4 min. Reduction of Area in %      - Hardness in BHN      - Impact in Joule      -	
Other	Other %	0.150 max.		
Aluminium	Al %	Balance		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
LM31	BS	British	Ingot and Casting
712.0	AA	USA	Casting
Al Zn5Mg	ISO	International	Ingot and Casting
712.0	SAE	USA	Casting
L-2710	UNE	Spain	Ingot and Casting
B-26 712.0	ASTM	USA	Casting
A-Z5G	AFNOR NF	France	Ingot and Casting

**Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email [marketing@gravitycastindia.com](mailto:marketing@gravitycastindia.com)**

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.