



Material - AS 1874 DA410

Standard Specification for Aluminium and Aluminium Alloys Ingot and Casting

Group - Non-Ferrous Aluminium Alloy

Sub Group - AS 1874 DA401 Aluminium and Aluminium Alloys - Ingot and Casting

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Ingot and Casting

Chemical Composition			Heat Treatment	
Copper	Cu %	0.600 max.	As-Cast	
Magnesium	Mg %	0.250 max.		
Silicon	Si %	10.000 - 13.000		
Iron	Fe %	1.000 max.		
Manganese	Mn %	0.500 max.		
Chromium	Cr %	0.100 max.		
Nickel	Ni %	0.500 max.		
Titanium	Ti %	0.200 max.		
Zinc	Zn %	0.400 max.		
Lead	Pb %	0.150 max.		
Tin	Sn %	0.150 max.	Mechanical Properties	
Other	Ot%	0.250 max.	Tensile Strength in Mpa	190 min.
Aluminium	Al %	Balance	Yield Strength in Mpa	-
-	-	-	Elongation in %	5 min.
-	-	-	Reduction of Area in %	-
			Hardness in BHN	-
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
AS401	AS	Australia	Ingot and Casting
A413.0	AA	USA	Ingot and Casting
AlSi12 (Fe)	ISO	International	Casting
ADC12	JIS	Japan	Casting
LM20	BS	British	Ingot and Casting
A413.0	NBR	Brazil	Ingot and Casting
A413.0	NMX	Maxico	Ingot and Casting

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.