



Material - AS 2738 C65500

Standard Specification for Copper and Copper Alloys - Compositions and Designations of Refinery Products, Wrought Products, Ingots and Castings

Group - Non-Ferrous Copper Alloy

Sub Group - AS 2738 Copper and Copper Alloys - Compositions and Designations of Refinery Products, Wrought Products, Ingots and Castings

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Ingot and Casting

Chemical Composition			Heat Treatment	
Iron	Fe %	0.800 max.	Normalizing or Annealing or Tempering	
Manganese	Mn %	0.500 - 1.300		
Nickel	Ni %	0.600 max.		
Lead	Pb %	0.050 max.		
Silicon	Si %	2.800 - 3.800		
Zinc	Zn %	1.500 max.		
Copper	Cu %	Balance		
-	-	-	Mechanical Properties Tensile Strength in Mpa 340 - 480 Yield Strength in Mpa - Elongation in % 15 - 50 Reduction of Area in % - Hardness in HV 85 - 100 Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B124 C65500	ASTM	USA	Rod, Bar and Shapes
B100 C65500	ASTM	USA	Plate and Sheet
B283 C65500	ASTM	USA	Forging
B96 C65500	ASTM	USA	Plate, Sheet, Strip and Bar
B98 C65500	ASTM	USA	Rod, Bar and Shape
SB-98 C65500	ASME	USA	Rod, Bar and Shape
SB-283 C65500	ASME	USA	Forging

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.