

Material - AS 2738 C85210

Standard Specification for Copper and Copper Alloys - Compositions and Designations of Refinery Products, Wrought Products, Ingots and Castings

Group - Non-Ferrous Copper Alloy

Sub Group - AS 2738 Copper and Copper Alloys - Compositions and Designations of Refinery Products, Wrought Products, Ingots and Castings

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Ingot and Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	0.005 max.		
Arsenic	As %	0.020 - 0.060		
Iron	Fe %	0.800 max.	As-Cast	
Nickel	Ni %	1.000 max.		
Lead	Pb %	2.000 - 5.000		
Silicon	Si %	0.005 max.		
Tin	Sn %	1.000 - 3.000		
Cu + Ni	Cu%+Ni%	70.000 - 75.000		-
Zinc	Zn %	Balance	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	170 min.
-	-	-	Yield Strength in Mpa	80 min.
-	-	-	Elongation in %	18 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HB	45 min.
-	-	-	Impact in Joule	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
SCB1	BS	British	Casting	
852C	AS	Australia	Ingot and Casting	
-	-	,	-	
-	-	-	-	
-	-	-	-	
-	-	-	-	
-	-	-	-	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.