



GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - AS 2738 C93700

Standard Specification for Copper and Copper Alloys - Compositions and Designations of Refinery Products, Wrought Products, Ingots and Castings

Group - Non-Ferrous Copper Alloy

Sub Group - AS 2738 Copper and Copper Alloys - Compositions and Designations of Refinery Products, Wrought Products, Ingots and Castings

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Ingot and Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	0.005 max.	As-Cast	
Iron	Fe %	0.150 max.		
Nickel	Ni %	0.500 max.		
Phosphorus	P %	0.100 max.		
Lead	Pb %	8.000 - 11.000		
Sulphur	S %	0.080 max.		
Antimony	Sb %	0.500 max.		
Silicon	Si %	0.005 max.		
Tin	Sn %	9.200 - 11.000		
Zinc	Zn %	0.800 min.		
Copper	Cu %	72.000 - 82.000	Mechanical Properties Tensile Strength in Mpa 190 - 280 Yield Strength in Mpa 80 - 160 Elongation in % 3 - 6 Reduction of Area in % - Hardness in HB 65 - 80 Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
LB2	BS	British	Casting
937B	AS	Australia	Ingot and Casting
CuPb10Sn10	ISO	International	Casting
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

ONE STOP SOLUTION FOR METAL PARTS