

## Material - AS 2738 C94100

Standard Specification for Copper and Copper Alloys - Compositions and Designations of Refinery Products, Wrought Products, Ingots and Castings

**Group - Non-Ferrous Copper Alloy** 

Sub Group - AS 2738 Copper and Copper Alloys - Compositions and Designations of Refinery Products, Wrought Products, Ingots and Castings

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Ingot and Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	0.005 max.		
Iron	Fe %	0.250 max.		
Nickel	Ni %	1.000 max.		
Phosphorus	P %	0.050 max.	As-Cast	
Lead	Pb %	18.000 - 22.000		
Sulphur	S %	0.080 max.		
Antimony	Sb %	0.800 max.		
Silicon	Si %	0.005 max.		-
Tin	Sn %	4.700 - 6.500	Mechanical Properties	
Zinc	Zn %	1.000 max.	Tensile Strength in Mpa	160 - 190
Copper	Cu %	72.000 - 79.000	Yield Strength in Mpa	60 - 100
-	-	-	Elongation in %	5 - 8
-	-	-	Reduction of Area in %	-
-	-	-	Hardn <mark>ess in HB</mark>	45 - 50
-	-		Impact in Joule	-

Cross Reference Table					
Material	Standard	Country	Grade Belong to the Industry		
LB 5	BS	British	Ingot and Casting		
941C	AS	Australia	Ingot and Casting		
CuPb20Sn5	ISO	International	Ingot and Casting		
-	-	-	-		
-	-	-	-		
-	-	-	-		
-	-	-	-		

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.