



Material - AS 6063

Standard Specification For Aluminium Alloy

Group - Non-Ferrous Aluminium Alloys Sub Group - AS 6063 Aluminium Alloy

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Wire, Rod, Bar and Strip

Chemical Composition			Heat Treatment	
Silicon	Si %	0.200 - 0.600		
Chromium	Cr %	0.100 max.	As Raw or Temper or Solution Treated or Aging	
Manganese	Mn %	0.100 max.		
Magnesium	Mg %	0.450 - 0.900		
Copper	Cu %	0.100 max.		
Iron	Fe %	0.350 max.		
Zinc	Zn %	0.100 max.		
Titanium	Ti %	0.100 max.		-
Other	Ot %	1.000 max.	Mechanical Properties	
Aluminium	AI %	Balance	Tensile Strength in Mpa	110 - 305
-	-	-	Yield Strength in Mpa	55 min.
-	-	-	Elongation in %	4 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
6063	SAE	USA	Bar, Rod, Shapes, Tube and Wire, Extrusion	
B 491 6063	ASTM	USA	Tube	
A96063	UNS	USA	Bar, Rod, Shapes, Tube and Wire, Extrusion	
EN AW-6063	DIN	Germany	Rod, Bar and Tube	
6063	ISO	International	Rod, Bar and Tube	
SB-241 6063	ASME	USA	Pipe and Tube	
B 275 GS10A	ASTM	USA	Bar, Rod, Shapes, Tube and Wire, Extrusion	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.